



## Tanalith E Recommended Retentions

### *PRESSURE TREATED TIMBER*

Full cell treatment of timber with moisture content < 28%

Country / Region	Hazard class 1 & 2	Hazard class 3 (NTR AB)	Hazard class 4 (NTR A)
EU	3,0 kg / m <sup>3</sup> wood	4,5 kg / m <sup>3</sup> wood	7,0 kg / m <sup>3</sup> wood